



METALLIC STANDARD COLORS



STERLING SILVER

PLANET BLUE

SILVERSIDE

RUSTIC BROWN



COPPER CANYON

CAPPUCCINO

BLUE SEA

PEARL

BLACK



ANTIQUÉ BRONZE

GOLD RUSH

SEDONA CLAY

RUBY RED

METALLIC WHITE

STANDARD APPLICATION

Preparation: Mechanically prepare surface to be porous & contaminant-free by diamond grinding or shot-blasting
Primer: Mix 1.5 gallons of BDC Epoxy Primer (1200 or Vapor Seal) with 1 large jar of BDC Metallic Pigment and apply @ 250-300 sq ft per 1.5 gal kit. Drill mix pigment into Resin first for better grinding of pigment.

Basecoat: Mix 1.5 gallons of Epoxy Basecoat (BDC 3300) with 1 large jar of BDC Metallic Pigment and apply with squeegee and backroll at 100-200 sq ft per kit. Immediately thereafter, do a minimum of 1 of the following steps:

- A) Finely mist denatured alcohol onto surface for mild effect
- B) Spray denatured alcohol with larger droplets onto surface for hammered metal effect
- C) Use a plastic loop roller cover to re-backroll for a textured effect
- D) Stream multiple colors onto surface and use a cordless leaf blower to move colors for a marbled effect.

Topcoat: Screen surface and apply clear topcoat (BDC 9700, 9750 or 9790 Polyaspartic, BDC 3100 or 3300 Epoxy, or BDC 9510 CRU)

* Colors displayed above are intended to provide an approximate representation. Colors may vary from batch to batch.